

### CLEAR NON BLOOM LOW ODOR ADHESIVE PART NO. 45005

#### DESCRIPTION

*Dynatex® Non Bloom/Low Odor Adhesive* is a single component low viscosity cyanoacrylate adhesive. No-odor and non-blooming characteristics make this product user friendly when vapor control is an issue.

#### PHYSICAL PROPERTIES

##### MONOMER (Liquid)

Base Compound .....	Ethoxyethyl Cyanoacrylate
Appearance.....	Colorless Liquid
Viscosity (cps @ 68°F) .....	5 cP
Specific Gravity (g/cc).....	1.06
Flash Point (TCC) .....	176°F
Shelf Life @ 40°F.....	One year in unopened containers
Military Specifications.....	None

#### CURING PROPERTIES

Ambient surface moisture will initiate the hardening process. Handling strength is reached in a short period of time and varies depending on environmental conditions and substrates being bonded. Product will continue to cure for at least 24 hours before full strength and resistances are developed.

##### Setting Time (68 F, 65% R.H.)

Steel .....	5 to 10 seconds
Aluminum .....	7 to 14 seconds
Neoprene.....	<8 seconds
ABS .....	5 to 10 seconds
Polycarbonate .....	10 to 20 seconds
PVC .....	5 to 10 seconds

#### CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

**POLYMER (Cured)**

Appearance.....	Colorless Solid
Service Temperature Range .....	-65 <sup>0</sup> F to 200 <sup>0</sup> F
Softening Point.....	293 <sup>0</sup> F
Refractive Index (ND 20) .....	1.49
Full Cure Time.....	24 Hours
Dielectric Strength KV/mm .....	12.6
Dielectric Constant @ 1Kc .....	5.4
Coefficient of Thermal Expansion (in./in./F) .....	.000126
Tensile Strength (Steel/Steel) .....	2400 psi
Solubility.....	Nitromethane, Acetone, Dimethylformamide

**Performance of Cured Materials**

(Tensile shear strength, cured for 48 hours @ 20-25<sup>0</sup>C (68-77<sup>0</sup>F)

<b>Substrate</b>	<b>Range in N/mm2</b>
Blasted Steel .....	16 to 20
Etched Aluminum.....	11 to 18
Neoprene .....	>10
ABS .....	>6
Polycarbonate.....	>5
PVC .....	>6

**CHEMICAL RESISTANCE**

Sheer strength on steel after 12 month soak

<b>Solvent</b>	<b>% Strength Retained</b>
Motor Oil .....	100
Gasoline .....	100
Trichloroethane.....	100
Freon TA .....	100
10% NaOH .....	0
10% Hcl .....	0
Water .....	0

**GENERAL DIRECTIONS**

1. Make sure the surfaces to be bonded are clean and dry.
2. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film after compression.
3. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute. (Maximum strength is attained in 24 hours.

4. Wipe off excess adhesive from the top of the container and recap. *Dynatex® Non Bloom/Low Odor Adhesive*, if left uncapped, may deteriorate by contamination from moisture in the air.
5. Because *Dynatex® Non Bloom/Low Odor Adhesive* condenses by polymerization, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

### **STORAGE**

Product should be stored unopened in a cool, dry place out of direct sunlight. Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

**For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**

### **USERS PLEASE READ**

The information and data contained herein is believed to be accurate and reliable; however, it the user's responsibility to determine suitable of use. Since the supplier cannot know all the uses, or the conditions of use to which there products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

The supplier warrants only that its products will meet its specifications. There is no use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product when to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.

**Dynatex®** A division of Accumetric, LLC

350 Ring Road Elizabethtown, Kentucky 42701 USA (800) 999-2937 TEL (270) 769-5557 FAX (270) 769-6418  
Outside U.S. TEL +1(270) 769-5557 FAX +1(270) 769-6418  
Email: sales@dynatexinc.com Website: www.dynatexinc.com